

## PRODUCT SPECIFICATION

Product code:

IXF-2CF-TmHo-PM-6-130

	Parameter	Specification	Units
1	Core diameter	$6 \pm 0.5$	$\mu\text{m}$
2	Clad diameter	$125 \pm 3$	$\mu\text{m}$
3	Coating diameter	$245 \pm 15$	$\mu\text{m}$
4	Core NA	$0.22 \pm 0.02$	
5	Cladding NA	$\geq 0.46$	
6	Clad absorption @790nm	$> 3.3$	dB/m
7	Clad absorption @1180nm*	$> 0.6$	dB/m
8	Multimode background losses	$< 50$	dB/km
9	Birefringence	$> 2 \cdot 10^{-4}$	
10	Core-clad offset	$< 1.0$	$\mu\text{m}$
11	Proof test level	100	kpsi

\*: Calculated from 1180 nm absorption value

### Comments

Panda PM design  
Round cladding shape  
HeNe multimode tested

Written by: A.LAURENT

Effective date of this document: 02/11/2017

Edition: A

Document reference: IXF-2CF-TmHo-PM-6-130\_edA.pdf

*Specifications are subject to change without notice*