

Industrial confidentiality

## PRODUCT SPECIFICATIONS

Product code: IXF-2CF-Yb-O-6-130-PF

	Parameter	Specification	Units
1	Core diameter	$6 \pm 0.5$	$\mu\text{m}$
2	Clad diameter (flat/flat)	$125 \pm 3$	$\mu\text{m}$
3	Coating diameter	$245 \pm 15$	$\mu\text{m}$
4	Core NA	$0.20 \pm 0.02$	
5	Cladding NA	$\geq 0.46$	
6	Clad absorption @915nm	$1.30 \pm 0.25$	dB/m
7	Clad absorption @976nm*	$5.2 \pm 1$	dB/m
8	Multimode background losses	$< 50$	dB/km
9	Core-clad offset	$< 1.0$	$\mu\text{m}$
10	Proof test level	100	kpsi

\*: Calculated from 915 nm absorption value

### Comments

Octagonal cladding shape  
HeNe multimode tested

Effective date of this document: 29/10/2018

Edition: A

Document reference: IXF-2CF-Yb-O-6-130-PF\_edA.pdf

*Specifications are subject to change without notice*

PSD-L-Q-E-086-I

