



**iXblue Polarization SCrambler  
PSC-LN**


# Introduction

The Lithium Niobate Integrated Optical Polarization Scrambler (PSC-LN) modulator is based on:

- A modified phase modulator on X-cut (low speed) or Z-cut (high speed)  $\text{LiNbO}_3$ .
- An optical waveguide made by titanium in-diffusion and supporting both TE- and TM-polarization states.
- An optical waveguide with a low Polarization Dependent Loss (PDL).
- An input polarization maintaining (PM) fiber whose slow axis is set at  $45^\circ$  from the TE and TM axis of the  $\text{LiNbO}_3$  crystal.
- An output standard single mode fiber.
- Lumped electrodes for low frequency applications (up to 200 MHz).
- Travelling wave electrodes for high frequency applications (up to 30 GHz).

# Principle

- The PSC-LN are based on a birefringent  $\text{LiNbO}_3$  phase modulator whose waveguide is illuminated at  $45^\circ$  of its main axis. The input state of polarization (SOP) is thus equally split up in two orthogonal TE and TM polarization states.
- Due to the birefringence properties of the  $\text{LiNbO}_3$  crystal (extraordinary and ordinary main axes) and the configuration of the modulator, the TE-polarized wave propagates at a different speed compared to the TM-polarized wave.
- When a voltage is applied via the control electrodes, an additional optical path difference between the TE and TM components is produced by the electro-optical effect, resulting in a new adjustable SOP for the output light (linear, circular or elliptic).



# Principle:

- Phase shift on the extraordinary fast axis:

$$\phi_e = \frac{2\pi}{\lambda} \left[ n_e L + \frac{1}{2} n_e^3 r_{33} l \eta \frac{V_0}{g} \right]$$

- Phase shift on the ordinary slow axis:

$$\phi_o = \frac{2\pi}{\lambda} \left[ n_o L + \frac{1}{2} n_o^3 r_{13} l \eta \frac{V_0}{g} \right]$$

- Differential phase shift:

$$\Delta\phi = \frac{2\pi}{\lambda} \left[ (n_e - n_o) L + \frac{1}{2} (n_e^3 r_{33} - n_o^3 r_{13}) l \eta \frac{V_0}{g} \right]$$



- Half-wave voltage  $V_\pi$  : voltage applied for a  $\pi$  radians phase shift between the fast and slow axes.

$$V_\pi = \frac{\lambda g}{(n_e^3 r_{33} - n_o^3 r_{13}) l \eta}$$

Symbol	Glossary
$n_e$	Extraordinary refractive index
$n_o$	Ordinary refractive index
$r_{13}, r_{33}$	LiNbO <sub>3</sub> Electro-optic coefficients
$L$	Crystal length
$l$	Electrode length
$g$	Electrodes gap
$\lambda$	Optical Wavelength
$V_0$	Applied Voltage
$\eta$	Electro-optic overlap

# Polarization on the Poincaré Sphere vs applied voltage

- When a variable voltage is applied on the electrodes, the output SOP follow a circle (red curve) whose trajectory crosses the states of right and left circular polarization and the two states of linear polarizations at  $\pm 45^\circ$ .
- Exemple of an experimental Poincaré sphere trace of the output SOP for a continuous voltage of  $10 V_{pp}$  applied to the modulator.  
PL denotes the linear polarisation states.



# Degree Of Polarization (DOP)

- On Lithium niobate modulators, the polarization scrambling method is based on applying a periodically voltage at a speed equal or higher than the bit rate.
- The degree of polarization (DOP) describes the portion of polarized light during the detection time frame.
- For the specific case of a periodically sinusoidal voltage applied on the electrodes:


$$V(t) = V_0 \sin(\Omega t)$$

$$\text{DOP} = |J_0(\gamma)|$$

with  $\gamma = \pi \frac{V_0 M(\Omega)}{V_\pi}$ , the modulation index.


$M(\Omega)$ , the electro-optic response of the modulator

- The DOP tends to zero at specific modulation indexes.
- For the first root:  $V_0 = 0,7655 V_\pi M(\Omega)$




# Configuration: Low frequency Polarisation Scrambler PSC-LN-0.1

- X-cut: better stability against environmental perturbations (temperature variations).
- Lumped electrodes: well adapted to the low frequency range (kHz, MHz).




*Simulated degree of polarization vs applied voltage*




# Configuration: High frequency Polarisation Scrambler PSC-LN-10

- Z-cut: high efficiency (low driving voltage).
- Travelling wave electrodes: very wide bandwidth (up to 30 GHz).
- Low electrical reflections ( $S_{11}$ ) thanks to travelling wave electrodes matched close to 50  $\Omega$ .



*Simulated degree of polarization vs electrical power*





# Conclusion

LiNbO<sub>3</sub> Integrated Optical Polarization Scrambler PSC-LN modulator features:

- Adjustable scrambling speed over a very wide range of frequencies.
- Compactness.
- Low electrical power consumption.
- Wide operating wavelength range.